

CUP/4STONE The experts in Natural Stone RAMILO ONLINE CATALOGUE ▣ Marie Contract Contra

INDEX

RAMILO

COLLECTION	6
Blanco Alpes	8
Blanquino	9
Gris Parga	10
Pedras Salgadas	11
Blanco Perla	12
Gris Tragal	13
Gris Perla	14
Crema Camelia	15
Amarillo Alpes	16
Crema Julia	17
Gris Alcántara	18
Silver Blue	19
Azul Platino	20
Azul Noche	21
Blue Pearl GT	22
Blue Pearl Royal	23
Emerald Pearl	24
Verde Oliva	25
Verde San Francisco	26
Baltic Brown	27
Antique Brown	28
Angola Black	29
Impala Black	30
Zimbabwe Black	31







FROM QUARRY TO CUSTOMER

CUPA STONE is the natural stone division of CUPA GROUP, a leading Spanish multinational in the roofing slate sector worldwide. Since the establishment of its first company, "RAMILO," in 1928, CUPA STONE has offered the widest range of products on the market, emphasizing sustainability, innovation, and personalized customer service.

For almost a century, CUPA STONE has been producing and distributing natural stone for exterior and interior applications and projects. The thirty branches and showrooms in Europe enable professionals to learn about various natural stone solutions that CUPA STONE provides, such as for facades, driveways, swimming pools, kitchens, bathrooms, roadways, and public gardens etc.



RAMILO, founded in 1928 in Vigo (Spain), is the production site of CUPA STONE and specializes in the transformation of granite blocks into slabs. We are pioneers in the exploitation and the expansion of national granites, collaborating with known architects on big international projects in cities such as New York, London, Paris, Singapore, and Tokyo. Over the last decade, Ramilo has been constantly working to improve its processes, incorporating new innovative machinery into its facilities, with the aim of always offering its customers the most advanced technologies and materials of the highest quality.




Our production facility is strategically located near the international port of Vigo and therefore connected to the rest of the world by sea. The continuous growth of RAMILO has enabled us to respond to the demand for our products from all over the world. We currently export to over 60 countries worldwide.

RAMILO is strongly committed to the achievement of the highest standards of environmental performance through the active minimization of the impact of our production processes. We recognize that our role is to make a difference today to create a better tomorrow.





Blanco Alpes



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS


Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption

2,610 Kg/m³ 147 MPa 10.4 MPa 0.3%

Blanquino



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,620 Kg/m³ 158 MPa 14.4 MPa 0.3%

Gris Parga



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption

2,620 Kg/m³ 164 MPa 11.5 MPa 0.2%

Pedras Salgadas



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS


Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption

2,618 Kg/m³ 101.57 MPa 16.68 MPa 0.21%

Blanco Perla



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,350 Kg/m³ 150 MPa 11.9 MPa 0.3%

Gris Tragal



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,640 Kg/m³ 165 MPa 15.9 MPa 0.3%

Gris Perla



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,650 Kg/m³ 177 MPa 8.9 MPa 0.3%

Crema Camelia



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,000 Kg/m³ 130 MPa 11.6 MPa 0.3%

Amarillo Alpes



FINISHES

Honed / Polished / Leather / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption

2,300 Kg/m³ 127 MPa 12 MPa 0.3%

Crema Julia



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,650 Kg/m³ 150 MPa 12.8 MPa 0.3%

Gris Alcántara



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption

0.3%

2,660 Kg/m³ 165 MPa 15,7 MPa

Silver Blue



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,660 Kg/m³ 157 MPa 14.9 MPa 0.2%

Azul Platino



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption

0.2%

2,640 Kg/m³ 139 MPa 14.1 MPa

Azul Noche



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,750 Kg/m³ 141 MPa 14.9 MPa 0.2%

Blue Pearl GT



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

251.8 MPa

APPLICATIONS

2,730 Kg/m³

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring


TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption

14.9 MPa

0.3%

Blue Pearl Royal



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,771 Kg/m³ 264 MPa 14.6 MPa 0.3%

Emerald Pearl



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS


Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption

2,699 Kg/m³ 174.8 MPa 12.5 MPa 0.16%

Verde Oliva



FINISHES

24

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,646 Kg/m³ 128 MPa 10.2 MPa 0.14%

Verde San Francisco



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,660 Kg/m³ 145 MPa 15.9 MPa 0.19%

Baltic Brown



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,680 Kg/m³ 162 MPa 10.1 MPa 0.1%

Antique Brown



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,700 Kg/m³ 100.94 MPa 7.7 MPa 0.13%

Angola Black



FINISHES

28

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,830 Kg/m³ 168 MPa 11.2 MPa 0.1%

Impala Black



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn


APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Cladding / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 2,940 Kg/m³ 240 MPa 22 MPa 0.13%

Zimbabwe Black



FINISHES

Honed / Polished / Leather / Aged / Flamed / Shot-blasted / Sawn

APPLICATIONS

Countertops / Interior Wall / Interior Flooring / Exterior Flooring

TECHNICAL INFORMATION

Specific weight Compressive strength Flexural strength Water absorption 3,066 Kg/m³ 270-287 MPa 31 MPa 0.13%

contact@cupastone.com www.cupastone.com CUP/4STONE RAMILO